

B6061

Fabric / Tissu / Weefsel / Gewebe	<i>DIN ISO 2060 : 1994</i>	100 % PES / 1100 dtex
Comment / Remarque / Opmerking / Kommentar		low wick
Total weight / Poids total / Gewicht totaal / Totalgewicht	<i>ISO 2286/2 : 2016</i>	1150 g/m²
Coating		PVC
Characteristics Caractéristiques Eigenschappen Eigenschaften		ABUV
Lacquering / Vernis / Lackierung		1/1
Embossing / Calandre / Kalander / Prägung		Dull
Breaking strength Warp Résistance rupture Chaîne Treksterkte Ketting Höchstzugkraft Kette	<i>ISO 1421/1 : 2016</i>	3800 N/5cm
Breaking strength Weft Résistance rupture Trame Treksterkte Inslag Höchstzugkraft Schuss	<i>ISO 1421/1 : 2016</i>	3500 N/5cm
Tear strength Warp Résistance à la déchirure Chaîne Scheurweerstand Ketting Weiterreisskraft Kette	<i>DIN 53363 : 2003</i>	550 N
Tear strength Weft Résistance à la déchirure Trame Scheurweerstand Inslag Weiterreisskraft Schuss	<i>DIN 53363 : 2003</i>	500 N
Adhesion / Adhérence / Hechting / Haftung	<i>ISO 2411 : 2017</i>	100 N/5cm
Gas permeability Perméabilité au gaz Gaspermeabilité Gaspermeabilität	<i>ISO 15105/1 : 2007 - DIN 53380/2 : 2006</i>	< 400 cm³/m².bar.d
Temperature resistance Tenue à la température Temperatuursbestendigheid Temperatursbeständigkeit	<i>EN 1876/1 : 1998</i>	-30/+70 °C
Light fastness (Except white and (half-)transparent) Tenue à la lumière (Excepté en blanc et (semi-)transparent) Lichtechtheid (Uitgezonderd wit en (half-)transparent) Lichtechtheit (Ausnahme weiss und (semi-)transparent)	<i>ISO 105 B02 : 2014</i>	7-8
Fire behaviour / Reaction au feu / Brandgedrag / Brennverhalten	<i>ISO 3795 : 1989</i>	< 100 mm/min

"Biogas fabrics are intended to be installed only by registered and experienced manufacturers of biogas installations, who are aware of the specifications and the limitations of the materials used. Direct contact of inner lung material with the reactive fermentation mixtures should be avoided. For further technical information on the membranes and its compatibility, we refer to the technical staff of Sioen Industries."

B6061

Application -> Agriculture/BiogasInstallation/HydrolysisResistant/FlexiTank

"Biogas fabrics are intended to be installed only by registered and experienced manufacturers of biogas installations, who are aware of the specifications and the limitations of the materials used. Direct contact of inner lung material with the reactive fermentation mixtures should be avoided. For further technical information on the membranes and its compatibility, we refer to the technical staff of Sioen Industries."