

Technical Data Sheet

Version 1 - Revision 10/02/2010

W60605300

6.0 X 6.0 PVC PLASTISOL T0/Z60

Fabric		100 % PES / 1100 dtex
Binding		1/1
Weight	<i>EN ISO 2286/2_2016</i>	255 [+/-10] g/m²
Construction Warp		6 thr/cm
Construction Weft		6 thr/cm
Fabric Weight	<i>EN ISO 2286/2_2016</i>	132 g/m²
Coating Weight	<i>EN ISO 2286/2_2016</i>	143 g/m²
Tensile Strength Warp	<i>NBN EN ISO 1421_2017</i>	>= 1600 N/5cm
Tensile Strength Weft	<i>NBN EN ISO 1421_2017</i>	>= 1600 N/5cm
Tensile Strength Elongation Warp	<i>NBN EN ISO 1421_2017</i>	> 15 %
Tensile Strength Elongation Weft	<i>NBN EN ISO 1421_2017</i>	> 15 %
Tear Strength Warp	<i>DIN 53363 2003</i>	> 400 N
Tear Strength Weft	<i>DIN 53363 2003</i>	> 400 N
Shrinkage at 200°C / 10 min. Warp	<i>DIN 53354 1981</i>	<= 4,5 %
Shrinkage at 200°C / 10 min. Weft	<i>DIN 53354 1981</i>	<= 2 %
Thickness	<i>EN ISO 2286/3_2016</i>	0,55 mm
Temperature Resistance	<i>DIN EN 1876/2 1998</i>	-30/+70 °C
Light Fastness (Except White)	<i>ISO 105 B02 2014</i>	6 - 8
Openess factor		10 %